



**TYPICAL PROPERTY DATA SHEET
BP RPP 1209 GR BIK**

Product Information:	12% glass reinforced polypropylene	Appearance:	Blk
Product Features:	Offers improved flex modulus while maintaining a low specific gravity properties Offers improved heat stability and scratch and mar resistance	Forms:	Strand cut Pellets
		Processing Method:	Processing Guide available upon request.

PHYSICAL	UNIT	OTHER INFORMATION	TEST METHOD	NOMINAL VALUES
MELT FLOW INDEX	g/10 min	can be adjusted for your injection or extrusion application.	ASTM D-1238	8-14
ASH	%		ASTM D-5630	10-14
SPECIFIC GRAVITY	g/cc		ASTM D-792	.97-.99
FLEX MODULUS	psi @ RT MPa	Minimum Value	ASTM D-790	375,000
NOTCHED IZOD	ft.lbs./in.		ASTM D-256	0.8

Typical values should not be construed as a guarantee analysis of any specific lot or as specification items. The properties of any single lot or shipment of product may vary from the above typical analysis. All information contained herein is accurate and to the best of our knowledge. However, Buckeye Polymers, Inc. assumes no liability, nor makes any guarantee to the accuracy or completeness of the information contained herein. Final determination as to the suitability of any information, or use of material, is solely the responsibility of the user.

Buckeye Polymers can custom compound a material to meet your specifications.

**Buckeye
Polymers, Inc.**

104 Lee Street
Lodi, Ohio 44254
Phone (330)948-3007
Fax (330)948-2037
www.buckeyepolymers.com