



**TYPICAL PROPERTY DATA SHEET  
BP RPP 2009 GK BLK**

<b>Product Information:</b> Our Glass Reinforced product lines exhibit increased tensile strength, stiffness, and heat deflection. Highly optimized glass reinforced PP resins have successfully replaced engineering thermoplastics in numerous applications. <b>Product Features:</b> * Good Flexural Strength	<b>Appearance:</b> BLACK  <b>Forms:</b> PELLET  <b>Processing Method:</b> INJ MOLD <b>Processing Guide available upon request.</b>
---	---

PHYSICAL	UNIT	OTHER INFORMATION	TEST METHOD	NOMINAL VALUES
MELT FLOW INDEX	g/10 min	can be adjusted for your injection or extrusion application.	ASTM D-1238	2 - 12
CARBON BLACK CONTENT	%			1
Glass Content	%			16 -22
FLEX MODULUS	psi @ RT MPa	Minimum Value	ASTM D-790	216,775min

Typical values should not be construed as a guarantee analysis of any specific lot or as specification items. The properties of any single lot or shipment of product may vary from the above typical analysis. All information contained herein is accurate and to the best of our knowledge. However, Buckeye Polymers, Inc. assumes no liability, nor makes any guarantee to the accuracy or completeness of the information contained herein. Final determination as to the suitability of any information, or use of material, is solely the responsibility of the user.

Buckeye Polymers can custom compound a material to meet your specifications.

**Buckeye  
Polymers, Inc.**

104 Lee Street  
Lodi, Ohio 44254  
Phone (330)948-3007  
Fax (330)948-2037  
[www.buckeyepolymers.com](http://www.buckeyepolymers.com)